

LOTRYL[®] BESTPEEL 2012

LOTRYL[®] BESTPEEL 2012 is a ready-to-use thermoplastic composition designed to make peelable heat seal layers onto various substrates. The base resin is a random ethylene-methyl acrylate copolymer.

- Used as top layer of laminates in order to provide the functions of heat sealability onto various substrates like PP, PS, PET and PVC, and easy opening by interfacial peeling. In the case of transparent structures, it maintains high clarity with low haze.
- Easily processed using the technologies of coextrusion coating, cast film coextrusion, blown film coextrusion or sheet coextrusion, to produce multilayers that can be used as lids, directly or after lamination with other films.

Typical Properties

	Test Method	Unit	Typical Value
Methyl Acrylate Content	FTIR (internal method)	%.-wt.	20
Melt Index (190°C/2.16kg)	ISO 1133 / ASTM D1238	g/10min.	11
Melting Point	ISO 11357-3	°C	79
Density	ISO 1193 / ASTM D150	g/cm ³	0.94
Vicat Softening Temperature (10N) ¹	ISO 306 / ASTM D1525	°C	42
Flexural Modulus ¹	ISO 178 / ASTM D790	MPa	25
Elongation at Break ¹	ISO 527-2 / ASTM D638	%	>700
Tensile Strength at break at 700% ¹	ISO 527-2 / ASTM D638	MPa	8.7
Hardness Shore A ¹	ISO 868 / ASTM D2240		84
Hardness Shore D ¹	ISO 868 / ASTM D2240		21
Haze ²	ASTM D1003	%	10

¹: On compression molded samples.

²: On 50µm monolayer film.

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Functional Polymer invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation assumes no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. SK Functional Polymer is a subsidiary of SK Global Chemical.

Processing

LOTRYL® BESTPEEL 2012 is processed with standard polyolefin extrusion equipment. It is not corrosive and its processability is similar to that of LDPE. Temperatures can be chosen in a very wide range. Usual recommendations start from 170°C in blown film extrusion, up to 300-310 °C in extrusion coating, thanks to the excellent heat stability of acrylate comonomer.

The composition of LOTRYL® BESTPEEL 2012 has been specifically designed to overcome the processing issues that are usually critical with tacky resins in film technologies, like chill roll release, blocking, bubble splitting and slip properties. LOTRYL® BESTPEEL 2012 is proposed as a ready-to-use resin with outstanding processability at both extrusion and downstream stages.

Purging LOTRYL® BESTPEEL 2012 is achieved with LDPE, and it is recommended to do it before shutdown.

Storage, Handling & Safety

LOTRYL® BESTPEEL 2012 should be stored in standard conditions and protected from UV-light. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Safety data sheet as well as information on handling and storage of the LOTRYL® BESTPEEL 2012 are available upon request to your SK Functional Polymer representative.

Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Functional Polymer invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation assumes no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. SK Functional Polymer is a subsidiary of SK Global Chemical.